

AD-A213 592 REPORT DOCUMENTATION PAGE

49

1a. RESTRICTIVE MARKINGS		1b. RESTRICTIVE MARKINGS	
UNCLASSIFIED		3. DISTRIBUTION/AVAILABILITY OF REPORT Available for public release. Distribution unlimited.	
2b. DECLASSIFICATION/DOWNGRADING SCHEDULE		5. MONITORING ORGANIZATION REPORT NUMBER(S) N00014-87-K0099	
4. PERFORMING ORGANIZATION REPORT NUMBER(S) Final Report		7a. NAME OF MONITORING ORGANIZATION Office of Naval Research	
6a. NAME OF PERFORMING ORGANIZATION Massachusetts Institute of Technology	6b. OFFICE SYMBOL (If applicable)	7b. ADDRESS (City, State, and ZIP Code) Polymer & Organic Chemistry Division Code 113P0, 800 North Quincy Street Arlington, VA 22217-5000	
6c. ADDRESS (City, State, and ZIP Code) Department of Chemistry, 6-331 77 Massachusetts Avenue Cambridge, MA 02139	8b. OFFICE SYMBOL (If applicable)	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER	
8a. NAME OF FUNDING/SPONSORING ORGANIZATION Office of Naval Research	8c. ADDRESS (City, State, and ZIP Code) US Navy Regional Finance Center CM #3, Room 206, Att: Code 40 Washington, DC 20371-5400	10. SOURCE OF FUNDING NUMBERS	
		PROGRAM ELEMENT NO.	PROJECT NO.
		TASK NO.	WORK UNIT ACCESSION NO.
11. TITLE (Include Security Classification) New Polymers Made with Well-Characterized Organometallic Catalysts			
12. PERSONAL AUTHOR(S) Richard R. Schrock			
13a. TYPE OF REPORT Final Report	13b. TIME COVERED FROM 2/1/89 TO 12/31/88	14. DATE OF REPORT (Year, Month, Day) October 16, 1989	15. PAGE COUNT
16. SUPPLEMENTARY NOTATION			
17. COSATI CODES		18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)	
FIELD	GROUP	SUB-GROUP	
19. ABSTRACT (Continue on reverse if necessary and identify by block number)			
<p>DTIC ELECTE OCT 24 1989 D & D</p>			
20. DISTRIBUTION/AVAILABILITY OF ABSTRACT <input checked="" type="checkbox"/> UNCLASSIFIED/UNLIMITED <input type="checkbox"/> SAME AS RPT. <input type="checkbox"/> DTIC USERS		21. ABSTRACT SECURITY CLASSIFICATION UNCLASSIFIED	
22a. NAME OF RESPONSIBLE INDIVIDUAL Richard R. Schrock		22b. TELEPHONE (Include Area Code) 617/253-1596	22c. OFFICE SYMBOL

DD FORM 1473, 84 MAR

83 APR edition may be used until exhausted.
All other editions are obsolete.

SECURITY CLASSIFICATION OF THIS PAGE

89 10 23 092

FINAL REPORT

Contract N00014-87-K0099

New Polymers Made with Well-Characterized Organometallic Catalysts

Richard R. Schrock, Department of Chemistry, 6-331, Massachusetts Institute of Technology,

77 Massachusetts Avenue, Cambridge, MA 02139

In the first publication we reported that $\text{Mo}(\text{CH-t-Bu})(\text{NAr})(\text{O-t-Bu})_2$ was a good catalyst for the ring opening metathesis polymerization of *endo,endo*-5,6-dicarbomethoxynorbornene to give homopolymers with polydispersities in the range 1.11-1.22, as well as block copolymers containing *endo,endo*-5,6-dicarbomethoxynorbornene and norbornene with similar low polydispersities.

In the second publication we reported additional details of the metathesis of functionalized monomers by molybdenum, and also that 7,8-bis(trifluoromethyl)tricyclo[4.2.2.0^{2,5}]deca-3,7,9-triene could be ring opened and the polymer cleaved with pivaldehyde to give (after pyrolysis) soluble polyenes, $(\text{t-Bu})(\text{CH}=\text{CH})_{2x+1}(\text{t-Bu})$. Triblocks containing a 40-ene (average) central chain, capped by two polynorbornene chains also were prepared.

In the third we applied some of the principles of Mo and W chemistry to Ta. $\text{Ta}(\text{CH-t-Bu})(\text{DIPP})_3(\text{THF})$ (**1**), $\text{Ta}(\text{CH-t-Bu})(\text{DMP})_3(\text{THF})$ (**3**; $\text{DMP} = \text{O-2,6-C}_6\text{H}_3\text{Me}_2$), and $\text{Ta}(\text{CH-t-Bu})(\text{TIPT})_3(\text{THF})$ (**5**; $\text{TIPT} = \text{S-2,4,6-C}_6\text{H}_2\text{-i-Pr}_3$) were prepared by straightforward methods. These species react with olefins to give metallacyclobutane intermediates, e.g., **1** reacts with norbornene to give an isolable tantalacyclobutane complex, $\text{Ta}[\text{CH}(\text{C}_5\text{H}_8)\text{CHCH}(\text{t-Bu})](\text{DIPP})_3$. Norbornene is polymerized by $\text{Ta}[\text{CH}(\text{C}_5\text{H}_8)\text{CHCH}(\text{t-Bu})](\text{DIPP})_3$ in a reaction that is zero order in norbornene to give essentially monodisperse polynorbornene. The TIPT system behaves similarly, and in this case secondary metathesis (after NBE has been consumed) is negligible. Several crystal structures were reported.

1A-1

In the fourth publication we reported that $\text{Ta}(\text{CHCMe}_3)(\text{DIPP})_3(\text{THF})$ ($\text{DIPP} = 2,6$ -diisopropylphenoxide) reacts with one equivalent of 2-butyne, diphenylacetylene, bis(trimethylsilyl)acetylene, or 2-methyl-1-buten-3-yne to give THF-free metallacyclobutene complexes, and that addition of pyridine to two of these metallacycles yields vinyl alkylidene complexes that react with up to 200 eq of 2-butyne readily to give living polymers. $\text{Ta}\{[\text{C}(\text{Me})\text{C}(\text{Me})]_x\text{CHCMe}_3\}(\text{DIPP})_3(\text{py})$, from which the organic polymer can be cleaved by treatment with benzaldehyde and shown to have a very low polydispersity (< 1.05). This work establishes that it is possible to polymerize acetylenes in a living fashion, and incorporate them into block copolymers made from cyclic olefins by ROMP.

In the fifth publication we examined potential chain transfer (CT) reagents for removing a growing polymer from living ROMP catalysts. Although 1-(2-cyclopentenylmethyl)-2-phenylethene will react with $\text{W}(\text{CH-t-Bu})(\text{NAr})(\text{O-t-Bu})_2$ to give $\text{W}(\text{CHPh})(\text{NAr})(\text{O-t-Bu})_2$ in 60% yield, other potential chain transfer (CT) reagents for W catalysts fail to varying degrees for a variety of reasons. The most significant problem is that the double bond in the alkenyl side chain of the alkenylcyclohexene (the rearrangement product of the CT reagent) ultimately reacts with a relatively small alkylidene ligand (e.g., a propylidene ligand) in the just-formed initiator. We conclude that although the principle is valid, the double bond in an ideal CT reagent would have to be considerably more reactive than that in a cyclopentene, and/or the catalyst would have to discriminate more efficiently between the double bond in the cyclic olefin and that in the side chain.

In the sixth publication we show that 5,6-dicarbomethoxynorbornadiene or 5,6-bis(trifluoromethyl)norbornadiene can be polymerized by $\text{Mo}(\text{CH-t-Bu})(\text{NAr})(\text{O-t-Bu})_2$ in a well-behaved living manner to give essentially monodisperse homopolymers that have a high degree of stereoregularity. Attempts to polymerize these monomers using $\text{W}(\text{CH-t-Bu})(\text{NAr})(\text{O-t-Bu})_2$ were unsuccessful.

Technical Reports and Published Articles:

1. "Low Polydispersity Homo- and Block Copolymers by Ring-Opening of 5,6-Dicarbomethoxynorbornene"
Murdzek, J. S.; Schrock, R. R. *Macromolecules* **1987**, *20*, 2640.
2. "Controlled Ring-opening Metathesis Polymerization by Molybdenum and Tungsten Alkylidene Complexes"
Schrock, R. R.; Krouse, S. A.; Knoll, K.; Feldman, J.; Murdzek, J. S.; Yang, D. C. *J. Mol. Catal.* **1988**, *46*, 243.*
3. "Preparation and Reactions of Tantalum Alkylidene Complexes Containing Bulky Phenoxide or Thiolate Ligands. Controlling Metathesis Activity and Mechanism Through Choice of Anionic Ligand."
Wallace, K. C.; Liu, A. H.; Dewan, J. C.; Schrock, R. R. *J. Am. Chem. Soc.* **1988**, *110*, 4964.*
4. "Living Polymerization of 2-Butyne Using a Well-Characterized Tantalum Catalyst"
Wallace, K. C.; Liu, A. H.; Davis, W. M.; Schrock, R. R. *Organometallics* **1989**, *8*, 644.
5. "An Evaluation of Cyclopentene-based Chain Transfer Agents for Living Ring Opening Metathesis Polymerization"
Schrock, R. R.; Yap, K. B.; Yang, D. C.; Sitzmann, H.; Sita, L. R.; Bazan, G. *Macromolecules* **1989**, *22*, 3191.

*Support by NSF DMR 84-18718 also acknowledged.

Names of Personnel:

J. S. Murdzek, R. R. Schrock, S. A. Krouse, K. Knoll, K. C. Wallace, K. B. Yap,
L. R. Sita, G. Bazan.